

---

**Product Description**

---

**ELOTEX<sup>®</sup> FLEX8310** is a redispersible binder based on the copolymer of acrylate.

Protective Colloid	Polyvinyl alcohol
Additives	Mineral anti-block agents
Plasticizers	none
Solvents	none
Film-forming agents	none

---

**Specifications**

---

Appearance	white, free-flowing powder
Bulk density	400 - 600 g/l
Residual moisture	< 2 %
Ash (DIN EN 1246 / 950 °C, 30 min)	9.5% +/- 1.25%
pH value	7.5 – 9.5 (as a 10% dispersion in water)
Glass transition temp.	approx. – 30°C
Min. film building temp.	approx. 0°C
Film properties	opaque, viscoplastic

---

**Application Areas**

---

Can be used to manufacture polymer-modified dry mixtures based on mineral binders such as cement, lime or gypsum.

**Main application areas**

- Low-temperature flexible sealing compounds
- Tile adhesives, flexibilized
- Anti-corrosion coatings

---

**Key Attributes**

---

**During processing**

- High saponification resistance
- Improved processing behaviour

**In the cure state**

- Improved adhesion to different base materials
- Highly improved flexibility, even at low temperatures such as approx. -25 °C
- Reduced water absorption
- Improved tensile bond strength and abrasion resistance
- Increased resistance against chemicals

---

**Powder Processing**

---

Elotex redispersible powders can be blended in all commercial positive mixers with other dry additives to produce finished products in powder form. Since Elotex redispersible powders exhibit thermoplastic behavior, mixing times should be as short as possible, and significant temperature rise caused by strong shear forces should be avoided. All hydraulically and non-hydraulically curing dry mixtures with Elotex redispersible powder may be easily mixed with water before application.

For mixing finished products in powder form, one usually places the required amount of mixing water in a suitable vessel and add the powder mixture under agitation. Too intensive agitation of the mixture may result in unwanted air inclusion.

---

**Packaging and Storage**

---

Standard packaging: 25 kg paper sacks with polyethylene liners.  
Other types of packaging such as Big Bags or silo wagons are possible on request.

As a basic rule it is recommended to store Elotex redispersible powder in a dry location at temperatures below 25°C and to process within six months. Sacks that are stored under pressure, damaged or left open for an extended period tend to cause blocking of the redispersible powder.

---

**Quality, Safety and Environment**

---

Elotex redispersible powders are non-toxic and are unclassified according to Regulation 88/379/EEC. We recommend all individuals using Elotex redispersible powder, or coming in contact with it, to observe the separate Safety Data Sheets. Our safety specialists will be pleased to advise you regarding safety, health and environmental issues of our products. Elotex has been certified according to DIN EN ISO9001 and DIN EN ISO14001.

---

**Product Liability**

---

The above information and recommendations are based upon our experience and are offered merely for advice. They do not absolve the consumer from making his own tests. Elotex AG, their representatives or distributor organizations have no control over the conditions under which Elotex redispersible powders are transported, stored, handled or used. Responsibility for damage arising from the use of our products cannot be derived from the recommendations given. The observance of any intellectual property rights of third parties is the responsibility of the consumer in each case.

Technical information may not be passed on to any third party without our previous consent.

---

**Other Information**

---

Version	3 / 25.5.2006
Replaces version from	1.9.2005
Date of first issue	15.8.2005
For regulatory information contact	Elotex AG/SA CH-6203 Sempach Station Phone +41 41 469 69 69 Fax +41 41 469 69 00 www.elotex.com <a href="mailto:contact.elotex@elotex.com">contact.elotex@elotex.com</a>

Elotex AG is a National Starch & Chemical Business